

# ARES

PORCELAIN COLLECTION





Ares Black Rectified Glazed Porcelain 24x48  
CERTAR2448BLK




Ares Gray Rectified Glazed Porcelain 24x48  
CERTAR2448GRY



Ares Brown Rectified Glazed Porcelain 24x48  
CERTAR2448BRN



Ares Ivory Rectified Glazed Porcelain 24x48  
CERTAR2448IVY












24" x 48"

Glazed / Matte / Coloredbody / Rectified

Product	Actual Piece Size (inch)	Thickness (inch)	pcs/box	sf/box	boxes/skid	sf/skid	lbs/skid
Ares Black Rectified Glazed Porcelain	23.62"x47.25"	0.413	2	15.50	27	418.50	2,092.50
Ares Gray Rectified Glazed Porcelain	23.62"x47.25"	0.413	2	15.50	27	418.50	2,092.50
Ares Brown Rectified Glazed Porcelain	23.62"x47.25"	0.413	2	15.50	27	418.50	2,092.50
Ares Ivory Rectified Glazed Porcelain	23.62"x47.25"	0.413	2	15.50	27	418.50	2,092.50

## TILE PERFORMANCE DATA

TECHNICAL CHARACTERISTICS	STANDARD METHOD	VALUES REQUIREMENTS
 CRAZING RESISTANCE BY AUTOCLAVE	ISO EN 10545-11	Resistant at 5 Atm for 2 hours
 SURFACE IMPACT RESISTANCE	ISO EN 10545-5	Not Damaged
 MODULUS OF RUPTURE	UNE-EN-ISO 10545-4	Min 40 N/mm <sup>2</sup>
 WATER ABSORPTION	ISO EN 10545-3	Max 0.5%
 FROST RESISTANCE	EN 10545-12	Not Damaged
 SURFACE ABRASION RESISTANCE	ISO EN 10545-7	P.E.I. III
 RESISTANCE TO CHEMICAL SUBSTANCES	ISO EN 10545-13	GLB, GHB
 RESISTANCE TO STAINING	ISO EN 10545-14	Class 5
 RESISTANCE TO THERMAL SHOCK	ISO EN 10545-9	Resistant