

VALLEY

PORCELAIN COLLECTION





Valley Ash Porcelain 6x36
CERTVY636A















Valley Natural Porcelain 6x36
CERTVY636N



Valley Random Porcelain 6x36
CERTVY636R



TILE PERFORMANCE DATA

TECHNICAL CHARACTERISTICS	STANDARD METHOD	VALUES	REQUIREMENTS
 CRACKING RESISTANCE	UNE-EN-ISO 10545-11	REQUESTED	PASSED
 HARDNESS	EN 101	Minimum 3	PASSED
 SLIP RESISTANCE	UNE-ENV 12633:2003	Available Method	Class 1
 RESISTANCE OF FLEXION	UNE-EN-ISO 10545-4	> 35 N/mm ²	PASSED
 BREAKING STRENGTH	UNE-EN-ISO 10545-4	> 1300 N	PASSED
 WATER ABSORPTION	UNE-EN-ISO 10545-3	≤0.50%	PASSED
 ACID RESISTANCE	UNE-EN-ISO 10545-13	Minimum GB	PASSED
 RESISTANCE TO FREEZE/TAW CYCLING	UNE-EN-ISO 10545-12	REQUESTED	PASSED
 SURFACE ABRASION	UNE-EN-ISO 10545-7	Class	PEI IV
 CHEMICAL RESISTANCE	UNE-EN-ISO 10545-13	Minimum GB	PASSED
 STAIN RESISTANCE	UNE-EN-ISO 10545-14	Minimum Class 3	PASSED
 ALKALINE RESISTANCE	UNE-EN-ISO 10545-13	GHA	PASSED